

GRADE		(EB-2015)		
STANDARD OF TEST		Q/320412 CNW 002-2015		
DENSITY	Kg/m ³	110-170	113.2	GB/T 6343-2009
TENSILE STRENGTH	Kpa	◦ 200	572.9	GB/T 6344-2008
COMPRESSION DEFLECTION	Kpa	◦ 20	46.7	ASTM D 1056
COMPRESSION DEFORMATION	%	■ 30	21.8	GB/T6669-2008
TEARING STRENGTH	N/m	◦ 400	572	GB/T10808-2006
HARDNESS	◦	10-20	15	C
120% 24h	%	----	11	GB/T 17794-2008
				